

Postal address: 82 Poštanski fah, Belgrade
Phone: +381 (11) 2833-686
Telephone: +381 (11) 2833-777, 2833-687, 2833-690
Fax: +381 (11) 2833-690
Marketing: 067/682-002
Tax ID (VAT No.): 100164792
Registration No.: 165-16855-17
TIN: 100164792



ATC
01-057

ACCREDITED
TESTING LABORATORY
SRPS ISO/IEC 17025:2006

Page 1 of 2

TEST REPORT No. 1216014

Client Name and Address : "DIG" DOO, BATAJNICA
Mladih gorana 12

Sample Description / Condition : FABRIC: ART. 2116 CORDURA

Sample Receipt Date : 02.07.2014.

Testing Performed : SAMPLE SUPPLIED

Testing Requested By : "DIG" DOO, BATAJNICA
ACCORDING TO JCI 36682/16.04.2014.

Test Results are Given in the Annex :

Total Number of Pages : 2

Report Verified By
Head of Laboratory

Ljiljana Parandilović, Dipl. Eng.



Report Approved By
Director of CIS Institute

Mr Mirjana Reljić, Dipl. Eng.

09.07.2014.

Report Issue Date

- * Testing is performed using standard laboratory equipment of CIS Institute.
- ** This document refers only to the tested sample.
- *** This document (or parts thereof) may not be reproduced, photocopied, or translated without prior written permission of CIS INSTITUTE Ltd., Belgrade.
- **** The signature confirms that testing results are recorded in laboratory working sheets.
The report is issued in 2 original copies.

Test Results:

Page 2 of 2

FABRIC: ART. "2116 CORDURA"

TEST ITEM	TEST METHOD	UNIT	RESULT
1. TOTAL WIDTH	ISO 22198:2006	cm	150
2. MASS PER UNIT AREA	ISO 3801:1977	g/m ²	212
3. BREAKING STRENGTH	SRPS EN ISO 13934-1:2008	N	
- in warp direction			2068
- in weft direction			1543
4. BREAKING ELONGATION	SRPS EN ISO 13934-1:2008	%	
- in warp direction			33
- in weft direction			38.2
5. YARN DENSITY	ISO 7211-2:1984	yarns/10 cm	
- warp yarns			195
- weft yarns			135
6. UNEQUAL YARN TENSION IN WARP AND WEFT			1.0
7. FIBER COMPOSITION		%	
- POLYAMIDE	ISO 1833-7:2006		100
8. SHRINKAGE AFTER WASHING AT 40 °C	ISO 5077:2007	%	
- in warp direction			-1.4
- in weft direction			+0.8
9. COLOUR FASTNESS TO: CHANGE / STAINING ON:		POLYAMIDE / WOOL	
- washing at 40 °C	ISO 105-C08:2008	rating	4/4/4
- perspiration - dry	ISO 105-X12:2001	rating	4-5
- perspiration - wet	ISO 105-X12:2001	rating	4-5
- ironing at 110 °C	ISO 105-X11:1994	rating	4/4
- dry cleaning: tetrachloroethylene	ISO 105-D01:2010	rating	4/4/4
- water	SRPS EN ISO 105-E01:2012	rating	4/4/4
- rubbing - alkaline	SRPS EN ISO 105-E04:2012	rating	4/4/4
- rubbing - acidic	SRPS EN ISO 105-E04:2012	rating	4/4/4
10. CARE INSTRUCTIONS	SRPS F.A0.011:2010		
- washing		Wash at temperature up to 40 °C	
- ironing		Iron at temperature up to 110 °C	
- dry cleaning		Dry cleaning with perchloroethylene allowed	
- drying		Drip dry, drip and line dry	
- bleaching		Do not bleach	

Test Performed By:

BA-07

PA-08

09.07.2014.

Date

Test Results Verified By

M.P.

Head of Laboratory

CIS-OB-17