



SPECIFICATION SHEET

ARTICLE		DUNAV	DISPERSE/INDANTREN
FABRIC DESCRIPTION			
FIBER COMPOSITION		EN ISO 1833	50/50 % CO/POLYESTER $\pm 3\%$
SPECIFIC WEIGHT		EN 12127	260 $\pm 5\%$
WEAVE		BDS 12674	RIPSTOP
YARN TYPE			COMBED
YARN COUNT	WARP	EN ISO 2060	tex 25 X 2 $\pm 2\%$
	WEFT		tex 40 X 1 $\pm 2\%$
NUMBER OF THREADS PER 10 CM	WARP	EN 1049-2	300 $\pm 3\%$
	WEFT		230 $\pm 3\%$
WIDTH		EN 1773	150 $\pm 2,5$ cm
PHYSICAL PERFORMANCES			
PARAMETER		TEST METHOD	RESULT
DIMENSIONAL STABILITY		EN ISO 5077	
	WARP	EN ISO 3759	max 2 %
	WEFT	EN ISO 6330	max 2 %
BREAKING STRENGTH (Strip Method)	WARP	EN ISO 13934-1	1200 N
	WEFT		700 N
RESISTANCE TO SURFACE WETTING (Spray test)		EN ISO 4920	min 3
OIL-REPELLENCY – Hydrocarbon resistance test		EN ISO 14419	min 3
COLOUR PERFORMANCES			
PARAMETER		TEST METHOD	RESULT
COLOUR FASTNESS TO RUBBING	DRY	EN ISO 105 X12	3-4
	WET		3
COLOUR FASTNESS TO WASHING (60°C)		EN ISO 105 C06	4
COLOUR FASTNESS TO ALKALINE PERSPIRATION		EN ISO 105 E04	4
COLOUR FASTNESS TO ACID PERSPIRATION		EN ISO 105 E04	4
COLOUR FASTNESS TO ARTIFICIAL LIGHT		EN ISO 105 B02	5

