

SPECIFICATION SHEET

ARTICLE		FRENKI water-repellent	DYED
FABRIC DESCRIPTION			
FIBER COMPOSITION		EN ISO 1833	67/33 % CO/POLYESTER ± 3 %
SPECIFIC WEIGHT		EN 12127	200 g/m ² ± 5 %
WEAVE		BDS 12674	RIPSTOP
YARN TYPE			COMBED
YARN COUNT	WARP	EN ISO 2060	tex 15 x 2 ± 2 %
	WEFT		tex 18 x 2 ± 2 %
NUMBER OF THREADS PER CM	WARP	EN 1049-2	36 ± 2
	WEFT		22 ± 2
WIDTH		EN 1773	150 ± 2,5 cm
PHYSICAL PERFORMANCES			
PARAMETER		TEST METHOD	RESULT
DIMENTIONAL STABILITY (60°C)	WARP	EN ISO 5077	max 2 % max 2 %
		EN ISO 3759	
	WEFT	EN ISO 6330	
BREAKING STRENGTH (Strip Method)	WARP	EN ISO 13934-1	80 daN
	WEFT		50 daN
COLOUR PERFORMANCES			
PARAMETER		TEST METHOD	RESULT
COLOUR FASTNESS TO WASHING (60°C)		EN ISO 105 C06	4/4/4
COLOUR FASTNESS TO ALKALINE PERSPIRATION		EN ISO 105 E04	4/4/4
COLOUR FASTNESS TO ACID PERSPIRATION		EN ISO 105 E04	4/4/4
COLOUR FASTNESS TO RUBBING	DRY	EN ISO 105 X12	3-4
	WET		3
COLOUR FASTNESS TO ARTIFICIAL LIGHT		EN ISO 105 B02	5